

KG105 Gasket Maker

Description

Krylex KG105 is a single component, low-medium strength, anaerobic gasketing compound. Krylex KG105 is a thixotropic product that is suitable for higher temperature applications. Krylex KG105 cures when confined in the absence of air between close-fitting flat metal surfaces.

Krylex KG105 is a 'form-in-place' gasketing product designed for use on rigid metal flanges and surfaces. Krylex KG105 is designed to withstand higher service temperatures than standard gasketing anaerobic products. Krylex KG105 develops low-medium strength. Krylex KG105 will give an almost instant low pressure seal (up to 0.5 bar after 20 mins.) to allow on-line pressure testing.

Typical Properties of Uncured Material

| | | |
|---------------------------|------------------------------|----------------|
| Chemical Type | | Dimethacrylate |
| Appearance | | Red-Orange |
| Specific Gravity | | 1.15 |
| Viscosity cPs | (Range) | 250,00-600,000 |
| | (Typical Value) | 425,000 |
| | (Range) ² | 40,000-80,000 |
| | (Typical Value) ² | 60,000 |
| Breakaway Torque (N.m) | range | 2-8 |
| | typical | N/A |
| Prevail Torque (N.m) | range | N/A |
| | typical | N/A |
| Fixture Time | (mins) | 20 |
| Full Cure @20°C | (hours) | 24 |
| Flash Point | (°C) | >100 |
| Max Gap Fill | (mm) | .50 |
| Operating Temp Range | (°C) | -50 to +150 |

Typical curing speed⁴, % of final strength:-

| | |
|----------|---------------|
| 20 mins | 5% strength |
| 3 hours | ~30% strength |
| 24 hours | 100% strength |

Cure Speed Influence

Cure speed and strength vary according to the substrates. When used on mild steel and brass components, anaerobic gasketing adhesives will reach full strength more rapidly than more inert materials such as stainless steel and zinc dichromate. Krylex Activators may be used to accelerate cure speed.

The size of the bond gap greatly affects the speed of cure of anaerobic adhesives. Bond gap varies with surface finish and flatness of flange. The larger the gap between mating surfaces, the slower the cure speed.

All figures relating to cure speed are tested at 22°C. Lower temperatures will result in a slower cure. Heating the assembled parts accelerates the curing process. Krylex Activators should be used when the temperature is less than 5°C.

When speed of cure is too slow or the bond gap is very large, Krylex Activators may be used to accelerate cure speed. The use of an accelerator may reduce bond strength by up to 30%. Chemence recommends testing on the parts to measure the effect.

Typical Environmental Resistance

Krylex anaerobic adhesives exhibit excellent chemical resistance to most oils and solvents including motor oil, leaded petroleum, brake fluid, acetone, ethanol, propanol and water. Anaerobic adhesives and sealants are not recommended for use in pure oxygen or chlorine lines.



CHEMENCE®

KG105

Gasket Maker

Instructions for Use

Ensure parts are clean, dry and free from oil and grease.

Apply adhesive to one side of flange. Assemble parts and allow curing. Wipe excess adhesive from outside of joint.

Product is normally hand applied from the bottle. Dispensing systems are available for high volume assembly applications. Please contact your Krylex representative for further advice on dispensing solutions.

Storage

Store in a cool area out of direct sunlight. Refrigeration to 5° gives optimum stability.

General Information

For safe handling of this product consult the Material Safety Data Sheet.

Anaerobic adhesives only cure in the absence of air and with metal part activation. Adhesive outside the joint will remain uncured and may be wiped away with a cloth.

Anaerobic adhesives are not recommended on certain plastics as stress cracking can sometimes result. Some anticorrosion chemicals inhibit the cure system in this type of anaerobic. Trials are recommended to establish whether cleaning of the parts are necessary. Krylex Activators may be required on plated parts and inactive metals.

Notes

The data contained in this data sheet may be reported as typical value and/or range. Values are based on actual test data and area verified on a regular basis.

Information presented herein has been compiled from sources considered to be accurate and reliable, but is not guaranteed to be so. Nothing herein shall be considered as recommending practices or products in violation of any patent, law or regulation. It is the user's responsibility to determine the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary. **WE MAKE NO WARRANTIES REGARDING THE PRODUCTS AND DISCLAIM ALL EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.**



CHEMENCE[®]