

KR016

Retaining Compound

Description

KR016 is a single component, low viscosity, general purpose, anaerobic retaining compound. KR016 is formulated for high strength bonding on close fitting cylindrical parts.

KR016 cures rapidly when confined in the absence of air on close-fitting metal surfaces.

KR016 prevents corrosion of assembled parts.

Typical Applications

KR016 is designed to augment the strength of cylindrical interference fit and press fit assemblies. Once applied, parts slip together easily, lubricated by the adhesive.

Typical applications include: bonding gears and pulleys on to shafts, bonding sleeves, pins and keys.

Technical Features

Chemical type:	Dimethacrylate
Appearance:	Green
State:	Liquid
Specific Gravity:	~1.07
Viscosity ¹ :	100 - 150 cPs
Breakaway Torque ² :	25 - 41 Nm
Prevail Torque ² :	25 - 40 Nm
Shear Strength ³ :	15 - 28 N/mm ²
Initial Fixture Time ⁴ :	≤15 minutes
Max. Gap Fill:	0.20 mm
Full Cure:	24 hours
Flash Point:	> 100 °C
Shelf Life:	12 months @ 20 °C
Operating Temp. Range:	-50 to +150 °C

¹ Brookfield LVF, spindle 2, speed 2.5 rpm

² On M10 black oxide steel bolt and M10 bright steel nut, ISO10964

³ On mild steel pin and collar, ISO10123

⁴ ISO 10964

Typical Curing Performance

Typical curing speed ⁴ as % of final strength.

Time	Value %
15 Minutes (Fixture time):	~10
1 hour:	~50
24 hours (Full cure):	100

Factors Affecting Cure Speed

Cure speed can be negatively influenced by very large gaps, low temperatures and can be dependent on the substrates being bonded.

Heating the assembled parts accelerates the curing process.

When used on mild steel and brass components, anaerobic adhesives will reach full strength more rapidly than more inert materials such as stainless steel and zinc dichromate.

Anaerobic adhesives only cure in the absence of air and with metal part activation.

Anaerobic activator KP6497 should be used on plated parts or when the temperature is less than 5°C. The use of an activator can reduce bond strength.

Some anti corrosion chemicals inhibit the cure system in this type of anaerobic. Trials are recommended to establish whether cleaning of the parts is necessary.

All figures relating to cure speed are tested at 21°C.

Chemence recommends testing the suitability of Krylex products for any specific application.

Chemical / Solvent Resistance

KR016 has good environmental resistance to water and other organic solvents including motor oil, ethanol and glycols.

KR016 is not recommended for use in pure Oxygen or Chlorine lines.

KR016

Retaining Compound

Typical Environmental Resistance

Hot strength: KR016 is suitable for use at temperatures up to 150°C. At 130°C the bond strength will be ~40% of the strength at 21°C.

Heat ageing: KR016 retains ~90% full strength when heated to 125°C for 90 days then cooled and tested at 21°C.

Limitations

KR016 is not recommended on certain plastics as stress cracking can sometimes result.

Instructions For Use

KR016 is suitable for high strength retaining applications that require minimal gap filling.

For best results, ensure parts are clean, dry and free from oil and grease.

KR016 adhesive should be applied manually to both surfaces.

Assemble parts use a rotating motion during assembly to ensure good coverage and allow to cure.

Wipe excess adhesive from outside of joint.

Product is normally hand applied from the bottle.

KR016 is suitable for use in dispensing systems for high volume assembly applications.

Storage

Optimal storage conditions are between 8°C and 21°C. Storage outside this temperature range can adversely affect product properties and may reduce the stated shelf life.

Please Note: When packed, KR016 requires an air space above the product to maintain stability.

Important: Product packed in bulk (>5kg) has a shelf life of 6 months. The material must be filled into smaller bottles / tubes within this time period.

General Information

For safe handling of this product consult the Safety Data Sheet.

Adhesive outside the joint will remain uncured and may be wiped away with a cloth.

Presentation

Bottles: 10ml, 50ml and 250ml.

Available in bulk for use with dispensing systems.

Notes

The data contained in this data sheet may be reported as typical value and / or range. Values are based on actual test data and are verified on a regular basis.

Disclaimer

Information presented herein has been compiled from sources considered to be accurate and reliable, but is not guaranteed to be so. Nothing herein shall be considered as recommending practices or products in violation of any patent, law or regulation. It is the user's responsibility to determine the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary.

WE MAKE NO WARRANTIES REGARDING THE PRODUCTS AND DISCLAIM ALL EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.